



Expanding Your Solutions

Corporate Headquarters

13191 Crossroads Pkwy N., Ste 325
City of Industry, CA 91746
Phone: 800.775.2362
Fax: 626.330.7598
www.cemcosteel.com

Manufacturing Facilities

City of Industry, CA
Denver, CO
Ft. Worth, TX
Pittsburg, CA

Structural Engineering/Design

1001-A Pittsburgh Antioch Hwy
Pittsburg, CA 94565
Phone: 800.775.2362
Fax: 626.330.7598
www.cemcoengineering.com

Technical Services

13191 Crossroads Pkwy N., Ste 325
City of Industry, CA 91746
Phone: 800.416.2278
Fax: 626.249.5004

362VT125-15 (25EQ) VIPERTRACK

Geometric Properties

3-5/8" X 1-1/4" flange 15 mil ViperTracks are manufactured from standard G40 hot-dipped galvanized steel. G60 and G90 coatings are available through special order, and may require up-charges and extended lead times.

Steel Thickness

Model No.	Design Thickness (in)	Minimum Thickness (in)	Yield (ksi)	Web Depth (W) (in)	Coating ⁴	Flange (in)
362VT125-15 (25EQ)	0.0155	0.0147	50	3-5/8	G40	1-1/4

Notes:

1. Uncoated steel thickness. Thickness is for carbon sheet steel.
2. Minimum thickness represents 95% of the design thickness and is the minimum acceptable thickness.
3. Per ASTM C645 & A1003.
4. G60 and G90 available upon request. Will require extended lead time and upcharge.

Color Code (painted on ends): 15 mil: None with Dark Grey band on pallet

ASTM & Code Standards:


- ASTM A653/A653M, A924/A924M, A1003/1003, C645 & C754
- ICC-ES & SFIA Code Compliance Certification Program
- ICC ESR-2620
- CBC: 2013, 2016, 2019
- IBC: 2012, 2015, 2018, 2021
- AISI: S100, S220
- ATI CCRR-0154

LEED v4 for Building and Design Construction

- MR Prerequisite: Construction and Demolition Waste Management Planning.
- MR Credit: Construction and Demolition Waste Management.
- MR Credit: Building Product Disclosure and Optimization – Sourcing of Raw Materials, Option 2.
- MR Credit: Building Product Disclosure and Optimization – Environmental Product Declarations, Options 1 & 2.
- MR Credit: Building Product Disclosure and Optimization – Material Ingredients, Option 1.
- MR Credit: Building Life-Cycle Impact Reduction, Option 4.

CEMCO cold-formed steel framing products contain 30% to 37% recycled steel.

- Total Recycled Content: 36.9%
- Post-Consumer: 19.8%
- Pre-Consumer: 14.4%



Interior Non-Load Bearing Track Section Properties

Member	Leg Size (in)					Gross Properties							Effective Properties			Torsional Properties				
		Weight (lb/ft)	Design (in)	Min (in)	Yield (ksi)	Area (in ²)	I _x (in ⁴)	S _x (in ³)	R _x (in)	I _y (in ⁴)	S _y (in ³)	R _y (in)	I _{xd} (in ⁴)	S _{xe} (in ³)	Ma (in-k)	X _o (in)	J _{x103} (in ⁴)	C _w (in)	R _o (in)	β
362VT125-15 (25EQ)	1.25	0.32	0.0155	0.0147	50	0.095	0.197	0.105	1.440	0.014	0.0139	0.381	0.115	0.039	1.15	-0.665	0.0076	0.035	1.63	0.833

Notes:

1. Section properties are in accordance with AISI S100 & S220.
2. Cold-work of forming is not included.
3. The effective moment of inertia for deflection is calculated based on AISI S100 & S220 procedure 1 for serviceability determination.
4. The center line bend radius is greater than 2 times the design thickness or 3/32".

Check the updated list of Certified Production Facilities at Intertek's website at <http://www.intertek.com/building/sfia>



This technical information reflects the most current information available and supersedes any and all previous publications effective October 10, 2022.

10-10-22 AT