

**Expanding Your Solutions** 

#### **Corporate Headquarters**

www.cemcosteel.com

13191 Crossroads Pkwy N., Ste 325 City of Industry, CA 91746 Phone: 800.775.2362 Fax: 626.330.7598

City of Industry, CA Denver, CO Ft. Worth, TX Pittsburg, CA

**Manufacturing Facilities** 

## Structural Engineering/Design

www.cemcoengineering.com

1001-A Pittsburgh Antioch Hwy Pittsburg, CA 94565 Phone: 800.775.2362 Fax: 626.330.7598

#### **Technical Services**

13191 Crossroads Pkwy N., Ste 325 City of Industry, CA 91746 Phone: 800.416.2278 Fax: 626.249.5004

# 362VT200-15 (25EQ) VIPERTRACK

#### **Geometric Properties**

3-5/8" ViperTrack with 2" legs is manufactured from standard G40 hot-dipped galvanized steel. G60 and G90 coatings are available through special order, and may require up-charges and extended lead times.

## **Physical Properties**

Model No.	Design Thickness (in)	Minimum Thickness (in)	<b>Yield</b> (ksi)	Coating <sup>3,4</sup>	Web Depth (in)	Leg Size (in)	GAP <sup>5</sup> (in)	Load <sup>5</sup> (lb.)	<b>Max Height</b> <sup>5</sup> 5 psf, 16" o.c.	
362VT200-15 (25EQ)	0.0155	0.0147	50	G40	3-5/8	2	1/2	34	10'-3"	

#### Notes

- 1. Uncoated steel thickness. Thickness is for carbon sheet steel
- 2. Minimum thickness represents 95% of the design thickness and is the minimum acceptable thickness.
- 3. Per ASTM C645 & A1003, Table 1.
- 4. G60 and G90 available upon request. Will require extended lead time and upcharge.
- 5. Use Gap, Load and Maximum Height data when member is used as a top deflection track.

Color Code (painted on ends): 15 mil: None with Dark Grey band on pallet

#### **ASTM & Code Standards:**

- ASTM A653/A653M, A924/A924M, A1003/A1003M, C645, C754, E119
- IBC: 2012, 2015, 2018, 2021
- CBC: 2013, 2016, 2019
- AISI: S100, S220

#### LEED v4 for Building and Design Construction

- MR Prerequisite: Construction and Demolition Waste Management Planning.
- MR Credit: Construction and Demolition Waste Management.
- MR Credit: Building Product Disclosure and Optimization Sourcing of Raw Materials, Option 2.
- MR Credit: Building Product Disclosure and Optimization Environmental Product Declarations, Options 1 & 2.
- MR Credit: Building Product Disclosure and Optimization Material Ingredients, Option 1.
- MR Credit: Building Life-Cycle Impact Reduction, Option 4.

## **CEMCO** cold-formed steel framing products contain 30% to 37% recycled steel.

■ Total Recycled Content: 36.9% ■ Post-Consumer: 19.8%

■ Pre-Consumer: 14.4%

CSI Division: 09.22.16 - Non-Structural Metal Framing

# (WEB DEPTH) 1-5/8", 2-1/2", 3-1/2" 3-5/8", 4", 5-1/2" & 6" STEEL DESIGN THICKNESS -(SEE TABLE) 1-1/2", 2", 2-1/2" & 3" -

# ViperTrack 2.00" Leg

						Gross Properties							Effective Properties			Torsional Properties				
Member	Leg Size (in)	Weight (lb/ft)	Design (in)	Min (in)	Yield (ksi)	Area (in²)	<b>lx</b> (in <sup>4</sup> )	Sx (in³)	Rx (in)	ly (in <sup>4</sup> )	Sy (in³)	Ry (in)	<b>lxd</b> (in <sup>4</sup> )	Sxe (in³)	Ma (in-k)	Xo (in)	<b>Jx1000</b> (in <sup>4</sup> )	Cw (in)	Ro (in)	ß
362VT200-15 (25EQ)	2.00	0.40	0.0155	0.0147	50	0.118	0.278	0.148	1.533	0.050	0.034	0.648	0.127	0.039	1.16	-1.28	0.0095	0.1220	2.10	0.629

#### Notes:

- 1. Section properties are in accordance with AISI S100 & S220.
- 2. Cold-work of forming is not included.

Facilities at Intertek's website at

3. The effective moment of inertia for deflection is calculated based on AISI S100 & S220 procedure 1 for serviceability determination.

4. The center line bend radius is greater than 2 times the design thickness or 3/32"





