

362VT200-33 VIPERTRACK

Geometric Properties

3-5/8" ViperTrack with 2" legs is manufactured from standard G40 hot-dipped galvanized steel. G60 and G90 coatings are available through special order, and may require up-charges and extended lead times.

Physical Properties

Model No.	Design Thickness (in)	Minimum Thickness (in)	Yield (ksi)	Coating ^{3,4}	Web Depth (in)	Leg Size (in)	GAP ⁵ (in)	Load ⁵ (lb.)	Max Height ⁵ 5 psf, 16" o.c.
362VT200-33	0.0346	0.0329	33	G40	3-5/8	2	1/2	112	33'-10"

Notes:

1. Uncoated steel thickness. Thickness is for carbon sheet steel.
2. Minimum thickness represents 95% of the design thickness and is the minimum acceptable thickness.
3. Per ASTM C645 & A1003, Table 1.
4. G60 and G90 available upon request. Will require extended lead time and upcharge.
5. Use Gap, Load and Maximum Height data when member is used as a top deflection track.

Color Code (painted on ends): 33 mil: White

ASTM & Code Standards:

- ASTM A653/A653M, A924/A924M, A1003/A1003M, C645, C754, E119
- IBC: 2012, 2015, 2018
- CBC: 2013, 2016
- AISI: S100-07, S100-12, S100-16, S220-11, S220-15


LEED v4 for Building and Design Construction

- MR Prerequisite: Construction and Demolition Waste Management Planning.
- MR Credit: Construction and Demolition Waste Management.
- MR Credit: Building Product Disclosure and Optimization – Sourcing of Raw Materials, Option 2.
- MR Credit: Building Product Disclosure and Optimization – Environmental Product Declarations, Options 1 & 2.
- MR Credit: Building Product Disclosure and Optimization – Material Ingredients, Option 1.
- MR Credit: Building Life-Cycle Impact Reduction, Option 4.

CEMCO cold-formed steel framing products contain 30% to 37% recycled steel.

- Total Recycled Content: 36.9%
- Post-Consumer: 19.8%
- Pre-Consumer: 14.4%

CSI Division: 09.22.16 – Non-Structural Metal Framing



ViperTrack 2.00" Leg

Member	Leg Size (in)	Gross Properties											Effective Properties			Torsional Properties				
		Weight (lb/ft)	Design (in)	Min (in)	Yield (ksi)	Area (in ²)	Ix (in ⁴)	Sx (in ³)	Rx (in)	Iy (in ⁴)	Sy (in ³)	Ry (in)	Ixd (in ⁴)	Sxe (in ³)	Ma (in-k)	Xo (in)	Jx1000 (in ⁴)	Cw (in)	Ro (in)	B
362VT200-33	2.00	0.90	0.0346	0.0329	33	0.264	0.626	0.330	1.540	0.110	0.075	0.644	0.455	0.191	3.76	-1.27	0.1050	0.2720	2.10	0.634

Notes:

1. Section properties are in accordance with AISI S100-16.
2. Cold-work of forming is not included.
3. The effective moment of inertia for deflection is calculated based on AISI S100-16 procedure 1 for serviceability determination.
4. The center line bend radius is greater than 2 times the design thickness or 3/32".