



Expanding Your Solutions

#### Corporate Headquarters

13191 Crossroads Pkwy N., Ste 325  
City of Industry, CA 91746  
Phone: 800.775.2362  
Fax: 626.330.7598  
www.cemcosteel.com

#### Manufacturing Facilities

City of Industry, CA  
Denver, CO  
Ft. Worth, TX  
Pittsburg, CA

#### Structural Engineering/Design

1001-A Pittsburgh Antioch Hwy  
Pittsburg, CA 94565  
Phone: 800.775.2362  
Fax: 626.330.7598  
www.cemcoengineering.com

#### Technical Services

13191 Crossroads Pkwy N., Ste 325  
City of Industry, CA 91746  
Phone: 800.416.2278  
Fax: 626.249.5004

## 600VT125-15 (25EQ) VIPERTRACK

### Geometric Properties

6" X 1-1/4" flange 15 mil ViperTracks are manufactured from standard G40 hot-dipped galvanized steel. G60 and G90 coatings are available through special order, and may require up-charges and extended lead times.

### Steel Thickness

Model No.	Design Thickness (in)	Minimum Thickness (in)	Yield (ksi)	Web Depth (W) (in)	Coating <sup>4</sup>	Flange (in)
600VT125-15 (25EQ)	0.0155	0.0147	50	6	G40	1-1/4

#### Notes:

- Uncoated steel thickness. Thickness is for carbon sheet steel.
- Minimum thickness represents 95% of the design thickness and is the minimum acceptable thickness.
- Per ASTM C645 & A1003.
- G60 and G90 available upon request. Will require extended lead time and upcharge.

**Color Code (painted on ends):** 15 mil: Dark Grey band on pallet

### ASTM & Code Standards:


- ASTM A653/A653M, A924/A924M, A1003/1003, C645 & C754
- ICC-ES & SFIA Code Compliance Certification Program
- ICC ESR-2620
- CBC: 2013, 2016, 2019
- IBC: 2012, 2015, 2018, 2021
- AISI: S100, S220
- ATI CCRR-0154

### LEED v4 for Building and Design Construction

- MR Prerequisite: Construction and Demolition Waste Management Planning.
- MR Credit: Construction and Demolition Waste Management.
- MR Credit: Building Product Disclosure and Optimization – Sourcing of Raw Materials, Option 2.
- MR Credit: Building Product Disclosure and Optimization – Environmental Product Declarations, Options 1 & 2.
- MR Credit: Building Product Disclosure and Optimization – Material Ingredients, Option 1.
- MR Credit: Building Life-Cycle Impact Reduction, Option 4.

**CEMCO cold-formed steel framing products contain 30% to 37% recycled steel.**

- Total Recycled Content: 36.9%
- Post-Consumer: 19.8%
- Pre-Consumer: 14.4%



### Interior Non-Load Bearing Track Section Properties

Member	Leg Size (in)						Gross Properties						Effective Properties			Torsional Properties				
		Weight (lb/ft)	Design (in)	Min (in)	Yield (ksi)	Area (in <sup>2</sup> )	I <sub>x</sub> (in <sup>4</sup> )	S <sub>x</sub> (in <sup>3</sup> )	R <sub>x</sub> (in)	I <sub>y</sub> (in <sup>4</sup> )	S <sub>y</sub> (in <sup>3</sup> )	R <sub>y</sub> (in)	I <sub>xd</sub> (in <sup>4</sup> )	S <sub>xe</sub> (in <sup>3</sup> )	Ma (in-k)	X <sub>o</sub> (in)	J <sub>x103</sub> (in <sup>4</sup> )	C <sub>w</sub> (in)	R <sub>o</sub> (in)	β
600VT125-15 (25EQ)	1.25	0.45	0.0155	0.0147	50	0.132	0.642	0.210	2.210	0.015	0.0146	0.342	0.325	0.063	1.90	-0.523	0.0106	0.109	2.29	0.948

#### Notes:

- Section properties are in accordance with AISI S100 & S220.
- Cold-work of forming is not included.
- The effective moment of inertia for deflection is calculated based on AISI S100 & S220 procedure 1 for serviceability determination.
- The center line bend radius is greater than 2 times the design thickness or 3/32".

Check the updated list of Certified Production Facilities at Intertek's website at <http://www.intertek.com/building/sfia>



This technical information reflects the most current information available and supersedes any and all previous publications effective October 10, 2022.

10-10-22 AT